



African Mineral Standards

MATRIX REFERENCE MATERIALS

Tel: +2711 923 8000 Fax: +2711 923 3924715 web: [www.amis.co.za](http://www.amis.co.za), D1 Isando Business Park,  
11 Gewel St (off Hulley Rd), Kempton Park, Johannesburg 1609. P.O. Box 856,  
Isando, 1600, South Africa, a division of the Set Point Group

## AMIS0111

### ***Certified Reference Material***

### **Gold and Uranium Ore Witwatersrand, South Africa**

### ***Certificate of Analysis***

### **Recommended Concentrations and Limits<sup>1</sup> (at two Standard Deviations)**

#### ***Certified Concentrations<sup>2</sup>***

Au Pb Collection	20.48	±	0.92	g/t
U M/ICP <sup>3</sup>	1048	±	109	ppm
U XRF <sup>3</sup>	1085	±	54	ppm
Specific Gravity	2.75	±	0.06	

1. Manufacturers recommended limits for use of the material as control samples, based on two standard deviations, calculated using "Between Laboratory" statistics for treatment of the data for trivial, non-trivial and technically invalid results. See sections 1, 9 and 12.
2. There is additional certified major element data presented on p2 and uncertified trace element data presented as an appendix.
3. Or, by applying a chemical conversion factor of  $U \times 1.1793 = U_{3O8}$ ;  $U_{3O8}$  by multi acid digestion:  $1236 \pm 129\text{ppm}$ ,  $U_{3O8}$  by XRF  $1280 \pm 64\text{ ppm}$ .

# Major Element Recommended Concentrations and Limits (at two Standard Deviations)

## ***Certified Concentrations***

Al <sub>2</sub> O <sub>3</sub>	2.04	±	0.04	%
CaO	0.24	±	0.02	%
Fe <sub>2</sub> O <sub>3</sub>	3.58	±	0.08	%
K <sub>2</sub> O	0.35	±	0.01	%
MgO	0.38	±	0.03	%
MnO	0.15	±	0.01	%
SiO <sub>2</sub>	90.59	±	0.92	%
TiO <sub>2</sub>	0.14	±	0.01	%

## ***Provisional Concentration***

Cr <sub>2</sub> O <sub>3</sub>	0.13	±	0.02	%
LOI	1.72	±	0.28	%

## ***Informational Mean***

Na <sub>2</sub> O	0.07	%
-------------------	------	---

1. **Intended Use:** AMIS0111 can be used to check the analysis of gold and uranium ores, hosted by siliceous rocks, with a similar grade and matrix..

It is a matrix matched Certified Reference Material, fit for use as control samples in routine assay laboratory quality control when inserted within runs of samples and measured in parallel to the unknown. Its purpose is to monitor inter-laboratory or instrument bias and within lab precision. It can be used, indirectly, to establish the traceability of results to an SI system of units.

The recommended concentrations and limits for this material are property values based on a measurement campaign (round robin) and reflect consensus results from the laboratories that participated in the round robin.

Slight variations in analytical procedures between laboratories will reflect as slight biases to the recommended concentrations (see 19). Good laboratories will report results within the two standard deviation levels with a failure rate of <10 %.

The material can also be used for method development and for the calibration of equipment.

2. **Origin of Material:** This standard is a blend of Ventersdorp Contact Reef, Carbon Leader Reef and Vaal Reef material provided by Anglo Gold Ashanti in South Africa. It was made from a mixture of pulp reject sample material, collected during routine underground sampling, sourced from mine assay laboratories and blended down to a required grade with silica.

3. **Approximate Mineral and Chemical Composition:** The major gangue mineral is quartz with minor pyrite, uraninite and thucolite. Gold occurs primarily as discrete grains. Trace element chemistry data from 12 of the labs has been compiled but has not been certified. Summary statistics for this data are set out in the appendix.

4. **Appearance:** The material is a very fine powder. It is colored a Light Grey (Corstor 5Y 7/1).

**5. Handling instructions:** The material is packaged in Laboratory Packs and Explorer Packs that must be shaken or otherwise agitated before use. Normal safety precautions for handling fine particulate matter are suggested, such as the use of safety glasses, breathing protection, gloves and a laboratory coat.

**6. Radioactivity:** Shipments of this material require special labeling and placarding. AMIS0111 contains U (13.5 Bq/g) and Th (0.4 Bq/g) and is classified as EXCEPTED MATERIAL in terms of "Safety Standards Series No. TS-R-1: Regulations for the Safe Transport of Radioactive Material, International Atomic Energy Agency, 2005, para 403, Table 1".

**7. Method of Preparation:** The material was crushed, dry-milled and air-classified to <54um. Wet sieve particle size analysis of random samples confirmed the material was 98.5% <54um. It was then blended in a bi-conical mixer, systematically divided and then sealed into 1kg Laboratory Packs. Explorer Packs are subdivided from the Laboratory packs as required. Samples were randomly selected for homogeneity testing and third party analysis. Statistical analysis of both homogeneity and the consensus test results were carried out by independent statisticians.

**8. Methods of Analysis requested:**

1. Au – Pb collection ICP-OES or ICP-MS.
2. Multi-acid digest, including HF, ICP- OES or ICP-MS. Multi element scan to include U.
3. U XRF.
4. Majors ( Al<sub>2</sub>O<sub>3</sub>, CaO, Cr<sub>2</sub>O<sub>3</sub>, Fe<sub>2</sub>O<sub>3</sub>, K<sub>2</sub>O, MgO, MnO, Na<sub>2</sub>O, SiO<sub>2</sub>, TiO<sub>2</sub>. LOI. ) XRF fusion.
5. SG ( gas pycnometer ).
6. Additionally, XRF analyses were requested for the major elements and a multi-element multi acid digest and ICP scan was requested for the trace elements.

**9. Information requested:**

1. State aliquots used for all determinations.
2. Report all results for gold and uranium in ppm.
3. All results for major elements to be reported as oxides in percentages.
4. All results for multi-element scans to be reported in ppm.
5. Report all QC data, to include replicates, blanks and certified reference materials used.
6. State and provide brief description of analytical techniques used.

**10. Method of Certification:** Twenty six laboratories were each given eight randomly selected packages of sample. Twenty five of the laboratories submitted results.

Final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was then removed from further calculations when the mean of all analyses from that laboratory failed a "t test" of the global means of the other laboratories. The means and standard deviations were then re-calculated using all remaining data. Any analysis that fell outside of the new two standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data.

The "between-laboratory" standard deviation is used in the calculation to eliminate technically and statistically invalid data. Upper and lower limits are based on the standard deviation of the remaining data, which reflect individual analyses and can be used to monitor accuracy in routine laboratory quality control. This is different to limits based on standard deviations derived from grouped set of analyses (see 12), which provide important measures for precision and trueness, but which are less useful for routine QC.

Standards with an RSD of near or less than 5 % are termed "Certified", RSD's of between near 5 % and 15 % are termed "Provisional", and RSD's over 15 % are termed "Informational".

**11. Participating Laboratories:** The 22 laboratories that provided results timeously were (not in same order as in the table of assays):

1. ALS Chemex Laboratory Group Brisbane Australia
2. ALS Chemex Laboratory Group Johannesburg SA
3. ALS Chemex Laboratory Group Lima (Peru)
4. ALS Chemex Laboratory Group Perth WA
5. ALS Chemex Laboratory Group Vancouver CA
6. Anglo Gold Ashanti - Navachab Gold Mine Laboratory Namibia
7. Anglo Gold Ashanti - Vaal River Laboratory SA
8. Anglo Research (Crown Campus)
9. Genalysis Laboratory Services (South Africa) Pty
10. Genalysis Laboratory Services WA
11. Goldfields Driefontein Assay Laboratory (South Africa)
12. Intertek Utama Services (Indonesia)
13. Performance Laboratories SA
14. Performance Labs (Welkom)
15. Set Point Laboratories (Isando) SA
16. SGS Australia Pty Ltd (Newburn) WA
17. SGS Mineral Services Callao (Peru)
18. SGS South Africa (Pty) Ltd - Booyens JHB
19. SGS Toronto (Canada)
20. Super Laboratory Services (Barberton SA)
21. Super Laboratory Services (Springs SA)
22. Ultra Trace (Pty) Ltd WA

**12. Assay Data:** Data as received from the laboratories for the important certified elements listed on p1 are set out below.

Lab Code	Au Pb coll ppm	U M/ICP ppm	U XRF ppm	Al2O3 XRF %	CaO XRF %	Cr2O3 XRF %	Fe2O3 XRF %	K2O XRF %	MgO XRF %	MnO XRF %	Na2O XRF %	SiO2 XRF %	TiO2 XRF %	LOI %	SG pycn
A	18.80														
A	19.82														
A	19.92														
A	20.76														
A	20.53														
A	20.91														
A	19.79														
A	19.74														
B	20.45		1123												
B	20.81		1123												
B	20.25		1127												
B	20.72		1127												
B	20.51		1126												
B	20.66		1126												
B	19.76		1126												
B	20.05		1125												
C	20.70	1120	1071	1.54	0.23	0.13	3.63	0.34		0.15	0.10	90.30	0.13	1.85	2.74
C	20.90	1128	1068	1.53	0.23	0.11	3.63	0.34		0.15	0.10	90.60	0.13	1.85	2.74
C	20.40	1106	1071	1.52	0.23	0.11	3.62	0.33		0.15	0.10	90.20	0.13	1.86	2.73
C	20.20	1129	1068	1.53	0.23	0.12	3.63	0.34		0.15	0.10	89.90	0.13	1.84	2.74
C	20.50	1108	1071	1.53	0.23	0.13	3.64	0.34		0.15	0.10	90.70	0.13	1.85	2.74
C	20.30	1127	1069	1.54	0.23	0.13	3.62	0.34		0.15	0.10	90.30	0.13	1.84	2.73
C	20.50	1125	1073	1.55	0.23	0.11	3.64	0.33		0.15	0.10	90.60	0.13	1.86	2.74
C	20.90	1128	1072	1.51	0.23	0.12	3.61	0.33		0.15	0.10	90.30	0.13	1.84	2.74
D															
D															
D															
D	18.30	1160	1130	2.00	0.25	0.14	3.59	0.36	0.39	0.15	0.07	89.80	0.13	1.72	
D	17.40	1170	1170	1.98	0.26	0.14	3.58	0.35	0.38	0.15	0.06	89.80	0.13	1.72	
D	18.00	1180	1170	2.00	0.26	0.14	3.58	0.35	0.38	0.15	0.06	89.80	0.13	1.80	
D	18.10	1150	1190	2.00	0.25	0.14	3.58	0.35	0.38	0.15	0.07	89.80	0.13	1.72	
D	18.60	1180	1160	2.00	0.25	0.14	3.59	0.35	0.37	0.15	0.06	89.80	0.13	1.72	
E	21.30														
E	19.90														
E	20.20														
E	22.10														
E	22.70														
E	20.60														
E	20.50														
E	20.80														
G	20.15	901													
G	20.55	883													
G	20.54	883													
G	20.34	882													
G	20.55	887													
G	20.19	896													
G	20.49	917													
G	20.55	886													

Assay data (cont)

Lab Code	Au Pb coll ppm	U M/ICP ppm	U XRF ppm	Al2O3 XRF %	CaO XRF %	Cr2O3 XRF %	Fe2O3 XRF %	K2O XRF %	MgO XRF %	MnO XRF %	Na2O XRF %	SiO2 XRF %	TiO2 XRF %	LOI %	SG pycn
H	20.70	1060	1078	2.08	0.27	0.15	3.61	0.38	0.46	0.16	0.07	90.90	0.13	2.15	2.70
H	20.30	1050	1074	2.04	0.26	0.14	3.57	0.38	0.44	0.15	0.08	89.90	0.13	2.01	2.71
H	20.70	1120	1076	2.06	0.27	0.14	3.54	0.38	0.45	0.15	0.09	88.90	0.13	2.09	2.72
H	20.90	1110	1085	2.07	0.26	0.14	3.50	0.37	0.43	0.16	0.07	90.80	0.13	1.90	2.77
H	20.60	1080	1086	2.06	0.29	0.14	3.62	0.39	0.43	0.15	0.07	90.50	0.13	2.20	2.73
H	20.40	1090	1082	2.05	0.26	0.14	3.57	0.38	0.43	0.15	0.06	90.20	0.13	2.23	2.71
H	20.60	1100	1085	2.07	0.27	0.15	3.65	0.38	0.43	0.15	0.07	91.10	0.14	1.97	2.71
H	20.90	1060	1080	2.04	0.26	0.14	3.64	0.37	0.42	0.15	0.07	89.30	0.13	2.14	2.71
I	19.48														
I	18.80														
I	21.92														
I	20.44														
I	19.68														
I	20.52														
I	19.00														
I	18.96														
J	19.80														
J	20.04														
J	18.69														
J	19.56														
J	18.21														
J	18.77														
J	18.37														
J	19.72														
K	21.40	1140	1140	2.05	0.25	0.14	3.58	0.35	0.38	0.15	0.08	90.95	0.14	1.52	2.82
K	21.80	1180	1130	2.05	0.25	0.14	3.57	0.35	0.38	0.15	0.08	91.10	0.14	1.49	2.82
K	21.20	1070	1140	2.06	0.25	0.14	3.58	0.35	0.38	0.15	0.09	91.03	0.14	1.50	2.80
K	20.50	1090	1140	2.07	0.25	0.14	3.58	0.35	0.38	0.15	0.09	90.98	0.14	1.51	2.81
K	21.20	1170	1140	2.06	0.25	0.14	3.59	0.35	0.39	0.15	0.09	91.02	0.14	1.53	2.79
K	20.80	1120	1140	2.06	0.25	0.14	3.58	0.35	0.38	0.15	0.09	91.12	0.14	1.48	2.78
K	20.60	1100	1140	2.05	0.24	0.14	3.58	0.35	0.39	0.15	0.09	90.97	0.14	1.49	2.81
K	21.40	1080	1120	2.06	0.25	0.14	3.57	0.35	0.38	0.15	0.09	91.02	0.14	1.52	2.79
L	19.90														
L	19.90														
L	19.84														
L	19.77														
L	19.76														
L	19.77														
L	19.83														
L	19.64														
M	20.74		1067												2.75
M	20.84		1084												2.77
M	20.97		1079												2.77
M	20.19		1084												2.75
M	20.81		1074												2.75
M	20.45		1085												2.74
M	20.80		1081												2.75
M	20.85		1087												2.76
N		990	1100	2.05	0.25	0.15	3.62	0.35	0.38	0.15		90.80	0.13	1.68	
N		970	1080	2.06	0.25	0.14	3.61	0.35	0.39	0.15		90.80	0.13	1.69	
N		1000	1100	2.08	0.24	0.14	3.62	0.35	0.40	0.15		90.80	0.13	1.70	
N		1000	1100	2.05	0.24	0.14	3.60	0.34	0.40	0.15		90.90	0.13	1.68	
N		1010	1080	2.05	0.24	0.14	3.59	0.34	0.39	0.15		90.90	0.13	1.64	
N		1020	1100	2.06	0.24	0.14	3.60	0.35	0.38	0.15		90.90	0.13	1.52	
N		990	1100	2.04	0.24	0.14	3.58	0.34	0.39	0.15		91.00	0.13	1.45	
N		1020	1100	2.05	0.25	0.14	3.62	0.34	0.40	0.15		91.00	0.14	1.45	
O	20.20	980	1115	1.94	0.24	0.13		0.33	0.35	0.14		88.50	0.13	1.74	
O	21.00	1010	1113	1.96	0.23	0.13		0.34	0.36	0.14		88.40	0.13	1.74	
O	21.10	1010	1144	1.96	0.24	0.12		0.33	0.35	0.14		88.50	0.13	1.74	
O	20.80	1000	1148	1.97	0.24	0.12		0.33	0.35	0.14		88.80	0.13	1.50	
O	21.10	990	1109	1.96	0.24	0.12		0.33	0.35	0.14		88.60	0.13	1.66	
O	21.10	990	1100	1.96	0.23	0.13		0.33	0.35	0.14		88.60	0.13	1.75	
O	20.90	990	1088	1.94	0.24	0.12		0.34	0.35	0.15		88.20	0.13	1.79	
O	21.20	990	1150	1.96	0.24	0.13		0.33	0.35	0.14		88.50	0.13	1.72	
P	20.60	1030	1035	2.04	0.23	0.13	3.50	0.35	0.39	0.15	0.06	90.55	0.13	1.97	2.79
P	20.90	1030	1045	2.02	0.23	0.13	3.54	0.35	0.38	0.15	0.06	90.43	0.13	1.96	2.74
P	20.80	1000	1040	2.02	0.23	0.13	3.53	0.35	0.39	0.15	0.06	90.55	0.13	1.97	2.74
P	20.90	1040	1045	2.04	0.22	0.13	3.52	0.35	0.38	0.15	0.07	90.49	0.13	2.00	2.85
P	20.50	1030	1035	2.03	0.23	0.13	3.54	0.35	0.40	0.15	0.07	90.39	0.13	1.95	2.70
P	20.80	1030	1045	2.04	0.23	0.13	3.54	0.35	0.39	0.15	0.06	90.61	0.13	1.97	2.80
P	21.00	1030	1045	2.03	0.23	0.14	3.51	0.35	0.39	0.15	0.06	90.52	0.12	2.01	2.73
P	20.70	960	1040	2.03	0.23	0.14	3.54	0.35	0.39	0.15	0.06	90.47	0.13	1.97	2.73
Q	20.50	1030		2.04	0.25	0.20	3.59	0.35	0.38	0.14	0.06	91.80	0.16	1.75	
Q	20.60	960		2.03	0.24	0.16	3.55	0.34	0.37	0.14	0.06	91.10	0.16	1.72	
Q	20.50	1040		2.03	0.24	0.19	3.58	0.34	0.37	0.14	0.05	91.40	0.16	1.73	
Q	20.60	1020		2.05	0.25	0.13	3.54	0.34	0.34	0.14	0.04	91.40	0.14	1.71	
Q	19.55	960		2.00	0.23	0.12	3.52	0.33	0.36	0.14	0.05	89.80	0.14	1.74	
Q	20.70	1060		2.01	0.23	0.12	3.50	0.34	0.35	0.14	0.05	89.90	0.14	1.75	
Q	20.30	1010		2.04	0.24	0.12	3.59	0.34	0.36	0.15	0.05	91.10	0.15	1.75	
Q	19.70	1020		2.03	0.24	0.13	3.60	0.34	0.37	0.15	0.06	91.50	0.15	1.76	

**Assay data (cont)**

Lab Code	Au Pb coll ppm	U M/ICP ppm	U XRF ppm	Al2O3 XRF %	CaO XRF %	Cr2O3 XRF %	Fe2O3 XRF %	K2O XRF %	MgO XRF %	MnO XRF %	Na2O XRF %	SiO2 XRF %	TiO2 XRF %	LOI %	SG pycn
R	20.00	1000	1090												2.76
R	19.90	1000	1085												2.76
R	20.20	1040	1090												2.74
R	20.80	1040	1085												2.76
R	19.50	1030	1095												2.74
R	20.10	1050	1085												2.74
R	20.50	1040	1085												2.74
R	19.15	1040	1090												2.78
S	19.70														
S	20.10														
S	20.40														
S	20.20														
S	19.60														
S	19.90														
S	19.60														
S	19.80														
T	21.01	1016	1072		0.25	0.13	3.48	0.36	0.37	0.14	0.06	89.87	0.14	1.63	2.45
T	20.57	1044	1062		0.25	0.13	3.47	0.35	0.37	0.14	0.05	89.88	0.14	1.65	
T	21.09	1024	1038		0.24	0.13	3.45	0.35	0.37	0.14	0.07	90.01	0.14	1.63	2.80
T	21.03	1005	1063		0.24	0.13	3.49	0.35	0.37	0.14	0.06	90.07	0.14	1.63	2.38
T	20.05	1023	1079		0.24	0.13	3.49	0.35	0.37	0.14	0.05	90.25	0.14	1.62	2.76
T	21.09	1032	1068		0.24	0.13	3.49	0.35	0.36	0.14	0.06	90.07	0.14	1.62	2.69
T	21.06	1029	1074		0.25	0.14	3.50	0.35	0.37	0.15	0.05	90.47	0.14	1.62	2.69
T	21.17	1052	1088		0.25	0.14	3.55	0.35	0.38	0.15	0.05	90.62	0.14	1.58	2.75
U	20.14														2.77
U	20.49														2.75
U	20.42														2.74
U	20.52														2.77
U	20.78														2.75
U	20.91														2.77
U	20.83														2.75
U	19.04														2.75
V	20.88														
V	21.06														
V	21.05														
V	20.86														
V	20.96														
V	20.88														
V	20.89														
V	20.94														
W	20.20			2.06	0.25	0.16	3.59	0.35	0.39	0.15	0.09	90.94	0.14	1.70	
W	20.10			2.04	0.24	0.14	3.53	0.35	0.38	0.15	0.08	90.85	0.14	1.70	
W	20.20			2.05	0.25	0.12	3.56	0.35	0.39	0.15	0.09	90.78	0.15	1.70	
W	20.40			2.03	0.25	0.13	3.57	0.35	0.39	0.15	0.08	90.87	0.15	1.80	
W	20.30			2.04	0.25	0.15	3.60	0.35	0.39	0.15	0.09	90.93	0.15	1.80	
W	19.80			2.03	0.25	0.13	3.57	0.35	0.39	0.15	0.08	90.75	0.14	1.80	
W	20.30			2.02	0.25	0.12	3.55	0.35	0.39	0.15	0.09	90.73	0.15	1.80	
W	20.20			2.05	0.25	0.14	3.57	0.35	0.40	0.16	0.09	90.93	0.14	1.80	

**13. Measurement of Uncertainty:**

The samples used in this certification process have been selected in such a way as to represent the entire batch of material and were taken from the final packaged units; therefore all possible sources of uncertainty (sample uncertainty and measurement uncertainty) are included in the final combined standard uncertainty determination.

The uncertainty measurement takes into consideration the between lab and the within lab variances and is calculated from the square roots of the variances of these components using the formula:

$$\text{Combined standard uncertainty} = \sqrt{(\text{between lab.var}/\text{no of labs}) + (\text{mean square within lab.var}/\text{no of assays})}$$

These uncertainty measurements may be used, by laboratories, as a component for calculating the total uncertainty for method validation according to the relevant ISO guidelines.

Analyte	Method	Unit	S <sup>1</sup>	$\sigma_L$ <sup>2</sup>	SW <sup>3</sup>	CSU <sup>4</sup>
Au	F	ppm	0.461	0.214	0.319	0.056
U	M/ICP	ppm	52.985	43.201	22.503	13.910
U	XRF	ppm	28.418	28.125	9.022	10.009
SG	pycnometer		0.033	0.022	0.026	0.008
Al <sub>2</sub> O <sub>3</sub>	XRF	%	0.020	0.018	0.012	0.007
CaO	XRF	%	0.008	0.007	0.004	0.002
Fe <sub>2</sub> O <sub>3</sub>	XRF	%	0.038	0.029	0.026	0.011
K <sub>2</sub> O	XRF	%	0.007	0.006	0.003	0.002
LOI		%	0.140	0.125	0.054	0.042
MgO	XRF	%	0.016	0.014	0.007	0.005
MnO	XRF	%	0.003	0.003	0.001	0.001
Na <sub>2</sub> O	XRF	%	0.017	0.017	0.006	0.006
P <sub>2</sub> O <sub>5</sub>	XRF	%	0.004	0.005	0.0017	0.002
SiO <sub>2</sub>	XRF	%	0.461	0.327	0.306	0.115
TiO <sub>2</sub>	XRF	%	0.007	0.005	0.003	0.002

1. S - Std Dev for use on control charts.
2.  $\sigma_L$  - Betw Lab Std Dev, for use to calculate a measure of accuracy.
3. SW - Within Lab Stc Dev, for use to calculate a measure of precision.
4. CSU - Combined Standard Uncertainty, a component for use to calculate the total uncertainty in method validation.

**14. Certified values:** The Certified, Provisional and Indicated values listed on p1 of this certificate fulfill the AMIS statistical criteria regarding agreement for certification and have been independently validated by Dr Barry Smee.

**15. Metrological Traceability:** The values quoted herein are based on the consensus values derived from statistical analysis of the data from an inter laboratory measurement program. Traceability to SI units is via the standards used by the individual laboratories the majority of which are accredited and who have maintained measurement traceability during the analytical process.

**16. Certification:** AMIS0111 is a new material.

**17. Period of validity:** The certified values are valid for this product, while still sealed in its original packaging, until notification to the contrary. The stability of the material will be subject to continuous testing for the duration of the inventory. Should product stability become an issue, all customers will be notified and notification to that effect will be placed on the [www.amis.co.za](http://www.amis.co.za) website.

**18. Minimum sample size:** The majority of laboratories reporting used a 0.5g sample size for the ICP and a 30g sample size for the fire assay. These are the recommended minimum sample sizes for the use of this material.

**19. Availability:** This product is available in Laboratory Packs containing 1kg of material and Explorer Packs containing custom weights (from 50 to 250g) of material. The Laboratory Packs are sealed bottles delivered in sealed foil pouches. The Explorer Packs contain material in standard geochem envelopes, nitrogen flushed and vacuum sealed in foil pouches.

**20. Recommended use:** The data used to characterize this CRM has been scrutinized using outlier treatment techniques. This, together with the number of participating laboratories, should overcome any "inter-laboratory issues" and should lead to a very accurate measure for the given methods, notwithstanding the underlying assumption that what the good inter-laboratory labs reported was accurate. However an amount of bad data might have had an effect, resulting in limits

which in some situations might be too broad for the effective monitoring of a single analytical method, laboratory or production process. Users should set their own limits based on their own data quality objectives and control measurements, after determining the performance characteristics of their own particular method, using a minimum of 20 analyses using this CRM. User set limits should normally be within the limits recommended on p1 and 2 of this certificate.

**21. Legal Notice:** This certificate and the reference material described in it have been prepared with due care and attention. However AMIS, Set Point Technology (Pty) Ltd, Mike McWha, Dr Barry Smee and Smee and Associates Ltd; accept no liability for any decisions or actions taken following the use of the reference material.

3 May 2010

**Certifying Officers:**



**African Mineral Standards:** \_\_\_\_\_

**Mike McWha**  
**BSc (Hons), FGSSA, MAusIMM, Pr.Sci.Nat**



**Geochemist:** \_\_\_\_\_

**Barry W. Smee**  
**BSc, PhD, P.Geo, (B.C.)**

### Appendix – uncertified trace element statistics

Analyte	Method	Unit	Mean	2SD	RSD%	n
Ag	M/ICP	ppm	2.2	0.4	8.5	60
Al	M/ICP	%	1.0	0.04	1.9	61
As	M/ICP	ppm	292	28	4.8	72
B	M/ICP	ppm	30.0	21.4	35.6	8
Ba	M/ICP	ppm	75.9	17.2	11.3	86
Be	M/ICP	ppm	0.56	0.13	11.4	73
Bi	M/ICP	ppm	1.7	0.2	5.6	71
Ca	M/ICP	%	0.18	0.02	6.8	86
Cd	M/ICP	ppm	0.54	0.07	6.8	71
Ce	M/ICP	ppm	66.8	5.7	4.3	68
Co	M/ICP	ppm	60.7	7.3	6.0	80
Cr	M/ICP	ppm	784	288	18.3	88
Cs	M/ICP	ppm	1.6	0.2	6.8	75
Cu	M/ICP	ppm	50.4	5.0	4.9	78
Dy	M/ICP	ppm	11.4	1.9	8.2	21
Er	M/ICP	ppm	5.7	1.1	9.2	21
Eu	M/ICP	ppm	1.3	0.1	5.4	20
Fe	M/ICP	%	2.5	0.3	5.1	88
Ga	M/ICP	ppm	3.2	0.5	7.7	66
Gd	M/ICP	ppm	9.2	1.6	8.7	21
Ge	M/ICP	ppm	0.10	0.07	36.1	45
Hf	M/ICP	ppm	3.3	1.3	19.9	69
Ho	M/ICP	ppm	2.1	0.4	9.0	21
In	M/ICP	ppm	0.020	0.003	8.6	62
K	M/ICP	%	0.28	0.03	5.3	83
La	M/ICP	ppm	34.8	6.2	8.9	85
Li	M/ICP	ppm	4.7	1.2	13.0	72
Lu	M/ICP	ppm	0.53	0.08	7.7	37
Mg	M/ICP	%	0.22	0.04	8.9	88
Mn	M/ICP	ppm	1158	103	4.4	82
Mo	M/ICP	ppm	4.3	0.6	7.4	82
Na	M/ICP	%	0.06	0.02	15.8	80
Nb	M/ICP	ppm	5.5	0.9	8.6	60
Nd	M/ICP	ppm	27.6	3.5	6.4	21
Ni	M/ICP	ppm	133	20	7.7	87
P	M/ICP	ppm	233	27	5.8	77
Pb	M/ICP	ppm	462	66	7.1	79
Pr	M/ICP	ppm	7.6	0.9	6.1	20
Rb	M/ICP	ppm	14.1	1.3	4.6	75
Re	M/ICP	ppm	0.003	0.002	23.7	35
S	M/ICP	%	1.2	0.1	4.2	69
Sb	M/ICP	ppm	6.0	1.0	8.2	79
Sc	M/ICP	ppm	3.0	0.3	5.3	54
Se	M/ICP	ppm	2.7	0.9	16.9	45
Si	M/ICP	%	43.7	0.5	0.6	8
Sm	M/ICP	ppm	7.6	1.1	7.4	21
Sn	M/ICP	ppm	1.8	0.3	8.1	69
Sr	M/ICP	ppm	22.6	2.2	4.9	79
Ta	M/ICP	ppm	2.0	1.0	25.0	68
Tb	M/ICP	ppm	1.8	0.2	6.4	36
Te	M/ICP	ppm	0.20	0.03	8.2	66
Th	M/ICP	ppm	105	11	5.2	68
Ti	M/ICP	%	0.06	0.02	15.5	80
Tl	M/ICP	ppm	0.15	0.03	10.9	64
Tm	M/ICP	ppm	0.79	0.15	9.7	21
V	M/ICP	ppm	16.0	4.6	14.5	80
W	M/ICP	ppm	0.83	0.34	20.3	77
Y	M/ICP	ppm	42.5	9.6	11.3	93
Yb	M/ICP	ppm	4.6	0.9	9.2	45
Zn	M/ICP	ppm	174	18	5.2	78
Zr	M/ICP	ppm	107	36	16.8	80