

**Witwatersrand High Ore Grade
Multi Element Reference Material
*Supplementary Certification for the Major Elements***

AMIS0029

Certificate of Analysis

**Recommended Concentration and two "Between Laboratory"
Standard Deviations**

Certified Concentrations

Al ₂ O ₃	5.42	+-	0.22%
CaO	0.316	+-	0.016%
Fe ₂ O ₃	5.252	+-	0.212%
K ₂ O	0.695	+-	0.042%
MgO	0.74	+-	0.04%
SiO ₂	84.08	+-	1.36%
SO ₃	3.78	+-	0.39%
TiO ₂	0.237	+-	0.018%

Provisional Concentrations

MnO	0.038	+-	0.006%
LOI	2.37	+-	0.24%

Indicated Mean

Na ₂ O	0.16%
P ₂ O ₅	0.042%

Intended use: AMIS0029 is suitable for monitoring the accuracy of a single analysis for the major elements in siliceous material. The material can be used for instrument calibration.

AMIS0029, has at the time of preparation of this certificate, also been certified for Au, Ag, U, Specific Gravity and the Rare Earth elements. This data is available on two separate certificates.

The recommended mean and "Between Lab" standard deviations for this standard reflect the average results from the laboratories that participated in the round robin. Slight variations in analytical procedures between laboratories will reflect as slight biases to the recommended concentrations and this is acceptable. Good laboratories however will report results within the two standard deviation levels with a failure of <10 %.

Origin of material: This standard was made from grade-sorted pulp rejects sourced from Anglo Gold Ashanti mine assay laboratories in South Africa. It represents sample material from the basal contacts of the Vaal Reef and the Carbon Leader Reef collected during routine underground sampling. This is primarily a multi-element gold standard, but at the request of customers and because of it's unusual character, it has also been certified for other elements.

Mineral and chemical composition: The other currently certified values for this material are:

Certified Concentrations*

Au (Pb Collection)	15.79	+ -	0.80 g/t
U (T/ICP)	867	+ -	72 ppm
U (XRF)	890	+ -	28 ppm
Specific Gravity	2.78	+ -	0.18 g/cc
Gd	8.98	+ -	1.02 ppm
La	42.93	+ -	4.82 ppm
Nd	32.88	+ -	3.75 ppm
Pr	8.77	+ -	1.03 ppm
Sm	8.46	+ -	0.90 ppm

Provisional Concentrations*

Ag (T)	2.1	+ -	0.6 ppm
Ce	82.77	+ -	13.76 ppm
Dy	10.45	+ -	1.51 ppm
Er	5.57	+ -	0.87 ppm
Eu	1.29	+ -	0.17 ppm
Ho	1.96	+ -	0.36 ppm
Lu	0.57	+ -	0.09 ppm
Tb	1.66	+ -	0.25 ppm
Tm	0.77	+ -	0.16 ppm
Yb	4.74	+ -	0.77 ppm

****Data for these other elements is available on separate certificates.***

Method of preparation: The material was crushed, dry-milled and air-classified to 100% <54µm. Wet sieve particle size analysis of random samples confirmed the material was 100% <54µm. It was then blended in a bi-conical mixer, systematically divided and then sealed into 1kg Laboratory Packs. Samples were randomly selected for homogeneity testing and third party analysis. Statistical analysis for the consensus test results were carried out by an independent statistician. Explorer Packs are subdivided from the Laboratory packs as required.

Methods of analysis requested:

1. Multi element XRF scan (to include U & rare earth elements).

Method of certification: Thirteen laboratories were each given eight randomly selected packages of sample. The results from the twelve laboratories that issued results timeously were used.

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards. Standards with an RSD of near or less than 5 % are certified, RSD's of between near 5 % and 15 % are Provisional, and RSD's over 15 % are Indicated.

Participating laboratories: (Not in same order as in the table of assays)

1. ACME Analytical Laboratories Ltd., (Canada).
2. ALS Chemex South Africa (Pty) Ltd.
3. ALS Chemex, (Vancouver, Canada).
4. Assayers Canada, (Vancouver).
5. Genalysis Laboratory Services (Pty) Ltd., (Australia).
6. Geoservice Centre, Geolaboratory, (GTK. Finland).
7. Pt Intertek Utama Services (Intertek, Indonesia)
8. Set Point Laboratories (Pty) Ltd (South Africa)
9. SGS Lakefield Research (Canada)
10. SGS Lakefield Research Africa (Pty) Ltd. (Joburg, South Africa)
11. SGS Welshpool (Australia).
12. Ultra Trace (Pty) Ltd. (Australia)

Assay Data: Data as received from the laboratories is set out below. A proficiency report has been sent to the managers of the participating laboratories.

AMIS0029 Major element analysis results

Lab Code	Percent Al2O3	percent CaO	Percent Fe2O3	Percent K2O	percent MgO	percent MnO	percent Na2O	percent P2O5	Percent SiO2	percent SO3	percent TiO2	Percent LOI
A	4.838	0.311	5.004	0.711	0.713	0.039	0.162	0.037	87.065		0.200	
A	4.744	0.369	4.904	0.711	0.696	0.039	0.162	0.039	85.140		0.200	
A	4.952	0.362	5.190	0.711	0.729	0.039	0.162	0.041	90.060		0.217	
A	4.952	0.404	5.147	0.687	0.729	0.039	0.148	0.039	88.777		0.217	
A	5.027	0.397	5.233	0.723	0.729	0.039	0.148	0.039	88.349		0.217	
A	4.876	0.347	5.047	0.699	0.713	0.039	0.162	0.041	87.493		0.217	
A	5.122	0.389	5.318	0.699	0.746	0.039	0.162	0.041	91.772		0.217	
A	5.405	0.372	5.390	0.699	0.779	0.039	0.148	0.039	92.841		0.234	
B	5.640	0.330	5.420	0.730	0.740	0.040	0.160	0.060	83.600	4.017	0.240	
B	5.560	0.320	5.410	0.720	0.730	0.040	0.160	0.050	83.890	4.117	0.240	
B	5.540	0.320	5.530	0.710	0.720	0.040	0.150	0.050	83.630	3.968	0.240	
B	5.510	0.330	5.310	0.720	0.730	0.040	0.160	0.050	84.120	3.968	0.240	
B	5.540	0.340	5.410	0.710	0.730	0.040	0.160	0.050	83.800	3.943	0.240	
B	5.520	0.320	5.470	0.720	0.730	0.040	0.150	0.060	83.750	3.893	0.240	
B	5.540	0.320	5.460	0.730	0.730	0.040	0.160	0.040	83.850	4.067	0.240	
B	5.540	0.330	5.470	0.730	0.740	0.040	0.160	0.040	84.060	3.893	0.240	
C	5.370	0.320	5.270	0.695	0.730	0.040	0.170		84.590	3.780	0.240	
C	5.350	0.320	5.240	0.694	0.730	0.040	0.170		84.400	3.760	0.240	
C	5.370	0.320	5.260	0.695	0.730	0.040	0.170		84.610	3.750	0.230	
C	5.380	0.320	5.280	0.696	0.730	0.040	0.170		84.740	3.730	0.240	
C	5.370	0.310	5.250	0.690	0.730	0.040	0.170		84.590	3.720	0.230	
C	5.400	0.320	5.260	0.694	0.730	0.040	0.170		84.590	3.740	0.240	
C	5.370	0.320	5.280	0.695	0.730	0.040	0.170		84.710	3.730	0.240	
C	5.370	0.320	5.270	0.693	0.730	0.040	0.170		84.640	3.780	0.240	
D												
D												
D												
D												
D												
D												
D												
D												
E	5.550	0.330	5.150	0.660	0.840	0.030	0.180	0.050	83.530	3.918	0.210	2.440
E	5.520	0.320	5.130	0.650	0.830	0.030	0.190	0.040	83.530	3.868	0.200	2.440
E	5.520	0.310	5.150	0.650	0.820	0.030	0.180	0.040	83.440	4.042	0.210	2.430
E	5.500	0.310	5.170	0.650	0.820	0.030	0.190	0.040	83.530	3.893	0.190	2.450
E	5.530	0.310	5.140	0.660	0.820	0.030	0.190	0.040	83.390	3.943	0.210	2.450
E	5.500	0.310	5.130	0.650	0.820	0.030	0.190	0.040	83.550	4.067	0.190	2.450
E	5.550	0.310	5.150	0.650	0.820	0.030	0.180	0.040	83.420	3.793	0.200	2.460
E	5.520	0.320	5.160	0.640	0.820	0.030	0.180	0.040	83.580	3.893	0.200	2.440
F	5.310	0.310	5.280	0.690	0.740	0.040	0.150	0.050	83.900	3.790	0.240	2.230
F	5.330	0.310	5.280	0.690	0.740	0.040	0.150	0.050	84.100	3.790	0.240	2.180
F	5.310	0.320	5.280	0.700	0.740	0.040	0.170	0.040	84.100	3.760	0.240	2.240
F	5.330	0.310	5.280	0.700	0.750	0.040	0.160	0.040	84.000	3.700	0.240	2.200
F	5.310	0.310	5.270	0.700	0.730	0.040	0.160	0.040	83.900	3.810	0.240	2.220
F	5.340	0.310	5.270	0.690	0.740	0.040	0.170	0.040	83.900	3.780	0.230	2.210
F	5.310	0.310	5.250	0.700	0.740	0.040	0.170	0.040	84.000	3.720	0.250	2.210
F	5.300	0.310	5.260	0.700	0.740	0.040	0.160	0.040	84.100	3.760	0.230	2.220
G	5.380	0.320	5.250	0.700	0.730	0.040	0.110	0.050	83.590	3.688	0.230	2.080
G	5.420	0.320	5.330	0.700	0.750	0.040	0.120	0.051	84.240	3.725	0.240	2.360
G	5.410	0.320	5.310	0.700	0.750	0.040	0.120	0.051	84.070	3.716	0.240	2.270
G	5.420	0.320	5.300	0.700	0.750	0.040	0.120	0.051	84.220	3.713	0.240	2.340
G	5.390	0.320	5.280	0.700	0.740	0.040	0.110	0.050	83.800	3.711	0.230	2.820
G	5.370	0.320	5.250	0.690	0.740	0.030	0.100	0.050	83.420	3.673	0.230	2.220
G	5.400	0.320	5.270	0.700	0.750	0.040	0.120	0.051	83.760	3.693	0.240	2.350
G	5.370	0.320	5.250	0.690	0.740	0.040	0.120	0.051	83.560	3.683	0.240	2.340
H	5.410	0.317	5.273	0.686	0.735	0.036	0.106	0.040	85.600	3.441	0.246	
H	5.420	0.314	5.284	0.687	0.725	0.035	0.103	0.043	85.600	3.431	0.249	
H	5.420	0.315	5.300	0.691	0.731	0.035	0.109	0.042	85.600	3.429	0.248	
H	5.410	0.314	5.269	0.682	0.722	0.036	0.096	0.038	85.300	3.426	0.246	
H	5.440	0.311	5.316	0.693	0.728	0.037	0.104	0.041	85.700	3.449	0.249	
H	5.390	0.318	5.287	0.687	0.730	0.035	0.105	0.042	85.500	3.429	0.246	
H	5.400	0.314	5.297	0.686	0.728	0.037	0.108	0.042	85.600	3.439	0.244	
H	5.450	0.314	5.298	0.686	0.732	0.035	0.111	0.042	85.800	3.446	0.247	
I	5.400	0.310	5.340	0.690	0.730	0.040	0.070	0.030	84.300		0.250	2.490
I	5.380	0.300	5.330	0.690	0.710	0.040	0.120	0.050	84.900		0.240	2.530
I	5.460	0.320	5.340	0.700	0.740	0.050	0.130	0.040	84.500		0.240	2.490
I	5.370	0.320	5.390	0.690	0.710	0.030	0.110	0.040	84.000		0.250	2.590
I	5.380	0.310	5.340	0.700	0.680	0.040	0.090	0.040	83.800		0.240	2.600
I	5.410	0.320	5.310	0.690	0.710	0.040	0.150	0.050	83.700		0.240	2.570
I	5.400	0.310	5.420	0.670	0.700	0.040	0.050	0.040	84.100		0.250	2.490
I	5.390	0.310	5.220	0.680	0.740	0.040	0.120	0.050	83.300		0.250	2.520


Lab Code	Percent Al2O3	percent CaO	Percent Fe2O3	Percent K2O	percent MgO	percent MnO	percent Na2O	percent P2O5	Percent SiO2	percent SO3	percent TiO2	Percent LOI
J	4.800	0.294	4.904	0.663	0.680	0.035	0.175	0.037		4.242	0.102	
J	4.895	0.294	4.990	0.675	0.696	0.036	0.202	0.037		4.292	0.117	
J	4.725	0.294	4.818	0.650	0.680	0.035	0.202	0.034		3.793	0.105	
J	4.744	0.280	4.804	0.638	0.680	0.035	0.202	0.034		3.768	0.117	
J	4.611	0.280	4.661	0.626	0.647	0.034	0.189	0.034		3.668	0.107	
J	4.819	0.280	4.932	0.650	0.680	0.035	0.189	0.037		3.918	0.108	
J	4.763	0.280	4.890	0.638	0.680	0.035	0.175	0.037		3.992	0.110	
J	4.611	0.280	4.789	0.638	0.663	0.035	0.175	0.034		3.843	0.102	
K	4.773	0.321	5.216	0.629	0.810	0.036	0.120	0.023	83.595	2.895	0.214	2.390
K	4.806	0.331	5.225	0.629	0.810	0.043	0.120	0.023	83.450	2.994	0.209	2.340
K	4.559	0.308	5.062	0.604	0.810	0.028	0.130	0.018	83.450	2.969	0.195	2.320
K	4.650	0.307	5.102	0.606	0.790	0.071	0.120	0.019	83.775	2.994	0.196	2.320
K	4.461	0.314	4.993	0.595	0.790	0.033	0.110	0.017	83.760	2.969	0.189	2.290
K	4.582	0.310	5.099	0.608	0.800	0.031	0.110	0.017	83.250	2.969	0.195	2.290
K	4.611	0.325	5.057	0.630	0.770	0.029	0.110	0.032	82.765	2.895	0.194	2.330
K	4.553	0.313	5.042	0.618	0.750	0.028	0.150	0.020	83.855	2.795	0.188	2.350
L	5.210	0.380	5.240	0.723	0.730	0.040	0.135	0.046	84.100	3.793	0.220	
L	5.300	0.400	5.270	0.723	0.730	0.040	0.135	0.041	85.600	3.818	0.230	
L	5.220	0.300	5.190	0.723	0.700	0.040	0.121	0.039	84.000	3.643	0.220	
L	5.140	0.270	5.090	0.723	0.680	0.040	0.135	0.044	82.700	3.818	0.220	
L	5.040	0.240	4.990	0.723	0.660	0.030	0.108	0.039	80.700	3.518	0.210	
L	5.360	0.500	5.270	0.723	0.740	0.040	0.148	0.039	85.600	3.793	0.230	
L	5.290	0.410	5.200	0.723	0.740	0.040	0.135	0.037	84.400	3.568	0.230	
L	5.310	0.350	5.390	0.723	0.710	0.040	0.121	0.032	85.800	3.219	0.230	
M	5.632	0.322	6.562	0.735	0.746	0.040	0.202		83.800		0.133	
M	5.632	0.322	6.634	0.747	0.763	0.040	0.189		83.700		0.150	
M	5.783	0.322	6.605	0.759	0.763	0.040	0.202		83.900		0.150	
M	5.764	0.322	6.634	0.759	0.763	0.040	0.202		84.000		0.150	
M	5.745	0.322	6.591	0.747	0.763	0.039	0.189		83.800		0.133	
M	5.783	0.322	6.634	0.747	0.763	0.040	0.189		83.800		0.133	
M	5.859	0.322	6.648	0.759	0.779	0.041	0.202		83.600		0.133	
M	5.896	0.336	6.648	0.759	0.779	0.040	0.202		83.900		0.133	

Availability: This product is available in Laboratory Packs containing 1kg of material or in Explorer Packs containing client specified weights of material from 50g up to 250g. Laboratory Packs are sealed bottles delivered in sealed foil pouches. Explorer Packs contain material in standard geochem envelopes placed into foil pouches that are nitrogen flushed and vacuum sealed.

Legal notice: This certificate and the reference material described in it have been prepared with due care and attention. However AMIS, Set Point Technology (Pty) Ltd, Mike McWha, Dr Barry Smee and Smee and Associates Ltd; accept no liability for any decisions or actions taken following the use of the reference material.

6 June 2007

Certifying officers:



African Mineral Standards: _____

Mike McWha
BSc (Hons), FGSSA, MSAIMM, Pr.Sci.Nat



Geochemist: _____

Barry W. Smee
BSc, PhD, P.Geo, (B.C.)